



TEST REPORT

Test Report # 18H-008788 Date of Report Issue: December 6, 2018
 Date of Sample Received: November 9, 2018 Pages: Page 1 of 35

CLIENT INFORMATION:

Company: Imagen Brands
 Recipient: Carissa Roepke
 Recipient Email: CarissaR@imagenbrands.com



SAMPLE INFORMATION:

Description:	Hyper Spinner, Caps Off Spinner, Fidget Spinner Pen, Caps Off Glow Spinner		
Assortment:	Black, Blue, Red, White, Green, Orange	Purchase Order Number:	-
SKU/style No.:	Refer to Page 2	Toy Co./Agency:	-
Factory/Supplier/Vendor:	LPP052158, DAP012900	Country of Origin:	China
Country of Distribution:	United States, Canada	Labeled Age Grade:	6+
Quantity Submitted:	Refer to Page 2	Recommended Age Grade:	Over 6 years of age
Testing Period:	11/27/2018 – 12/05/2018	Tested Age Grade:	Over 6 years of age

OVERALL RESULT:



Refer to page 3 for test result summary and appropriate notes.

ANSECO GROUP (HK) LIMITED

Loska Yeung Lok Ka
Assistant Manager, Chemical Laboratory

ANSECO GROUP (HK) LIMITED

Ricky Cheung Chin Yeung
Manager, Physical Laboratory

ANSECO GROUP (HK) LIMITED ♦ 3/F Liven House ♦ No. 61 – 63 King Yip Street ♦ Kwun Tong ♦ Kowloon ♦ Hong Kong ♦ Tel: (852)3185 8000

The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.

The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.

This test report may not be reproduced in whole or in part, without written approval of ANSECO Group (HK) Limited.

ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.

**SKU/STYLE NO./ QUANTITY SUBMITTED DETAILED:**

Style description	SKU No.	Style No.	Qty.
Hyper Spinner	CPCR006-BK	CPCR006	8 pcs
	CPCR006-BL	CPCR006	8 pcs
	CPCR006-RD	CPCR006	8 pcs
	CPCR006-WH	CPCR006	8 pcs
Caps Off Spinner	CPCR007-BK	CPCR007	8 pcs
	CPCR007-BL	CPCR007	8 pcs
	CPCR007-RD	CPCR007	8 pcs
	CPCR007-WH	CPCR007	8 pcs
Fidget Spinner Pen	CWTG012-BK	CWTG012	8 pcs
	CWTG012-BL	CWTG012	8 pcs
	CWTG012-GR	CWTG012	8 pcs
	CWTG012-OR	CWTG012	8 pcs
	CWTG012-RD	CWTG012	8 pcs
Caps Off Glow Spinner	CPCR015-WH	CPCR015	8 pcs
Dry paint	-	-	1 lot

**TEST RESULTS SUMMARY:**

At the request of the client, the following tests were conducted:

CONCLUSION	TEST(S) CONDUCTED
PASS	CPSIA Section 106 & ASTM F963-17 Toy Safety, Clause 4.3.5 Soluble Elements in Paints and Similar Surface Coatings
PASS	CPSIA Section 106 & ASTM F963-17 Toy Safety, Clause 4.3.5 Soluble Elements in Substrate Materials
PASS	CPSIA Section 101 & 16 CFR 1303, Total Lead in Paints and Surface Coatings
PASS	California Proposition 65, Total Lead in Paints and Surface Coatings
PASS	CPSIA Section 101, Total Lead in Substrate Materials
PASS	California Proposition 65, Total Lead in Substrate Materials
PASS	California Proposition 65, Phthalates (DBP, BBP, DEHP, DINP, DIDP, DnHP)
PASS	16 CFR 1307 Prohibition of Children's Toys and Child Care Articles Containing Specified Phthalates (DBP, BBP, DEHP, DINP, DHEXP / DnHP, DCHP, DIBP, DPENP) [#]
PASS	Canadian Toys Regulations SOR/2011-17 as Amended, Item 23 – Leachable Elements in Paints and Surface Coatings
PASS	Canadian Toys Regulations SOR/2011-17 as Amended, Item 23 – Total Lead and Mercury in Paints and Surface Coatings
PASS	Canadian Consumer Products Containing Lead Regulations (SOR/2018-83), Total Lead Content
PASS	CPSIA Section 106, Mandatory Toy Safety Standard ASTM F963-17, Mechanical Hazards 16 CFR 1500, Federal Hazardous Substances Act (FHSA), Mechanical Hazards
PASS	16 CFR 1500.44 and ASTM F963-17, Section 4.2, Flammability of Solids
PASS	19 CFR 134.11, Country of Origin [#]
PASS	Canadian Toy Regulations SOR/2011-17 as Amended by SOR/2016-195 & SOR/2016-302, Mechanical Hazards Requirements
PASS	Canadian Toy Regulations SOR/2011-17 as Amended by SOR/2016-195 & SOR/2016-302, Item 21 Celluloid or Cellulose Nitrate

**DETAILED RESULTS:****CPSIA Section 106 & ASTM F963-17 Toy Safety, Clause 4.3.5 Soluble Elements in Paints and Similar Surface Coatings**

Test Method: ASTM F963-17 Clause 8.3.2

Analytical Method: Inductively Coupled Plasma-Mass Spectrometry

Specimen No.	1	2	3	4	---	Soluble Limit (ppm)
Test Item	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	
Soluble Antimony (Sb)	ND	ND	ND	ND	---	60
Soluble Arsenic (As)	ND	ND	ND	ND	---	25
Soluble Barium (Ba)	ND	ND	ND	ND	---	1000
Soluble Cadmium (Cd)	ND	ND	ND	ND	---	75
Soluble Chromium (Cr)	ND	ND	ND	ND	---	60
Soluble Lead (Pb)	ND	ND	ND	ND	---	90
Soluble Mercury (Hg)	ND	ND	ND	ND	---	60
Soluble Selenium (Se)	ND	ND	ND	ND	---	500
Conclusion	PASS	PASS	PASS	PASS	---	

Note:

ppm (Parts per million) = mg/kg (Milligrams per kilogram)

LT = Less than

ND = Not detected (Reporting Limit = 2 ppm)

Remark:

Test portion of Specimen No. 1 found on single sample was 10.0 mg.

Test portion of Specimen No. 2 found on single sample was 10.4 mg.

Test portion of Specimen No. 3 found on single sample was 30.1 mg.

Test portion of Specimen No. 4 found on single sample was 31.0 mg.

**DETAILED RESULTS:****CPSIA Section 106 & ASTM F963-17 Toy Safety, Clause 4.3.5 Soluble Elements in Substrate Materials**

Test Method: ASTM F963-17 Clause 8.3.5

Analytical Method: Inductively Coupled Plasma-Mass Spectrometry

Substrate Materials Other than Modeling Clay

Specimen No.	5	6	7	8	9	Soluble Limit (ppm)
Test Item	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	
Soluble Antimony (Sb)	ND	ND	ND	ND	ND	60
Soluble Arsenic (As)	ND	ND	ND	ND	ND	25
Soluble Barium (Ba)	ND	ND	ND	ND	ND	1000
Soluble Cadmium (Cd)	ND	ND	ND	ND	ND	75
Soluble Chromium (Cr)	ND	ND	ND	ND	ND	60
Soluble Lead (Pb)	ND	ND	ND	ND	ND	90
Soluble Mercury (Hg)	ND	ND	ND	ND	ND	60
Soluble Selenium (Se)	ND	ND	ND	ND	ND	500
Conclusion	PASS	PASS	PASS	PASS	PASS	

Note:

ppm (Parts per million) = mg/kg (Milligrams per kilogram)

LT = Less than

ND = Not detected (Reporting Limit = 2 ppm)

**DETAILED RESULTS:****CPSIA Section 106 & ASTM F963-17 Toy Safety, Clause 4.3.5 Soluble Elements in Substrate Materials**

Test Method: ASTM F963-17 Clause 8.3.5

Analytical Method: Inductively Coupled Plasma-Mass Spectrometry

Substrate Materials Other than Modeling Clay

Specimen No.	10	11	12	13	14	Soluble Limit (ppm)
Test Item	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	
Soluble Antimony (Sb)	ND	ND	ND	ND	ND	60
Soluble Arsenic (As)	ND	ND	ND	ND	ND	25
Soluble Barium (Ba)	ND	ND	ND	ND	ND	1000
Soluble Cadmium (Cd)	ND	ND	ND	ND	ND	75
Soluble Chromium (Cr)	ND	ND	ND	ND	ND	60
Soluble Lead (Pb)	ND	ND	ND	ND	ND	90
Soluble Mercury (Hg)	ND	ND	ND	ND	ND	60
Soluble Selenium (Se)	ND	ND	ND	ND	ND	500
Conclusion	PASS	PASS	PASS	PASS	PASS	

Note:

ppm (Parts per million) = mg/kg (Milligrams per kilogram)

LT = Less than

ND = Not detected (Reporting Limit = 2 ppm)

Remark:

Test portion of Specimen No. 13 found on single sample was 83.0 mg.

**DETAILED RESULTS:****CPSIA Section 106 & ASTM F963-17 Toy Safety, Clause 4.3.5 Soluble Elements in Substrate Materials**

Test Method: ASTM F963-17 Clause 8.3.5

Analytical Method: Inductively Coupled Plasma-Mass Spectrometry

Substrate Materials Other than Modeling Clay

Specimen No.	15	16	17	18	19	Soluble Limit (ppm)
Test Item	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	
Soluble Antimony (Sb)	ND	ND	ND	ND	ND	60
Soluble Arsenic (As)	ND	ND	ND	ND	ND	25
Soluble Barium (Ba)	ND	ND	ND	ND	ND	1000
Soluble Cadmium (Cd)	ND	ND	ND	ND	ND	75
Soluble Chromium (Cr)	ND	ND	ND	ND	ND	60
Soluble Lead (Pb)	ND	ND	ND	ND	ND	90
Soluble Mercury (Hg)	ND	ND	ND	ND	ND	60
Soluble Selenium (Se)	ND	ND	ND	ND	ND	500
Conclusion	PASS	PASS	PASS	PASS	PASS	

Note:

ppm (Parts per million) = mg/kg (Milligrams per kilogram)

LT = Less than

ND = Not detected (Reporting Limit = 2 ppm)

Remark:

Test portion of Specimen No. 19 found on single sample was 93.9 mg.

**DETAILED RESULTS:****CPSIA Section 106 & ASTM F963-17 Toy Safety, Clause 4.3.5 Soluble Elements in Substrate Materials**

Test Method: ASTM F963-17 Clause 8.3.5

Analytical Method: Inductively Coupled Plasma-Mass Spectrometry

Substrate Materials Other than Modeling Clay

Specimen No.	20	21	24	---	---	Soluble Limit (ppm)
Test Item	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	
Soluble Antimony (Sb)	ND	ND	ND	---	---	60
Soluble Arsenic (As)	ND	ND	ND	---	---	25
Soluble Barium (Ba)	ND	ND	ND	---	---	1000
Soluble Cadmium (Cd)	ND	ND	ND	---	---	75
Soluble Chromium (Cr)	ND	ND	ND	---	---	60
Soluble Lead (Pb)	ND	ND	ND	---	---	90
Soluble Mercury (Hg)	ND	ND	ND	---	---	60
Soluble Selenium (Se)	ND	ND	ND	---	---	500
Conclusion	PASS	PASS	PASS	---	---	

Note:

ppm (Parts per million) = mg/kg (Milligrams per kilogram)

LT = Less than

ND = Not detected (Reporting Limit = 2 ppm)

Remark:

Test portion of Specimen No. 24 found on single sample was 48.8 mg.



DETAILED RESULTS:

CPSIA Section 101 & 16 CFR 1303, Total Lead in Paints and Surface Coatings

Test Method: CPSC-CH-E-1003-09.1

Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	1	2	3	4	---	Total Limit (ppm)
Test Item	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	
Total Lead (Pb)	ND	ND	ND	ND	---	90
Conclusion	PASS	PASS	PASS	PASS	---	

Note:

ppm (Parts per million) = mg/kg (Milligrams per kilogram)

LT = Less than

ND = Not detected (Reporting Limit = 20 ppm)

Composite results are based on specimen of least mass resulting in highest potential concentration.

The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.

The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.

This test report may not be reproduced in whole or in part, without written approval of ANSECO Group (HK) Limited.

ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.



DETAILED RESULTS:

California Proposition 65, Total Lead in Paints and Surface Coatings

Test Method: CPSC-CH-E-1003-09.1

Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	1	2	3	4	---	Total Limit (ppm)
Test Item	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	
Total Lead (Pb)	ND	ND	ND	ND	---	90
Conclusion	PASS	PASS	PASS	PASS	---	

Note:

ppm (Parts per million) = mg/kg (Milligrams per kilogram)

LT = Less than

ND = Not detected (Reporting Limit = 20 ppm)

Composite results are based on specimen of least mass resulting in highest potential concentration.

Remark:

The specification is quoted from client's requirement.

**DETAILED RESULTS:****CPSIA Section 101, Total Lead in Substrate Materials**

Test Method: CPSC-CH-E1001-08.3 (Metal), CPSC-CH-E1002-08.3 (Non-Metal)

Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	5	6	7	8	9	Total Limit (ppm)
Test Item	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	
Total Lead (Pb)	ND	ND	ND	ND	ND	100
Conclusion	PASS	PASS	PASS	PASS	PASS	

Specimen No.	10	11	12	13	14	Total Limit (ppm)
Test Item	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	
Total Lead (Pb)	ND	ND	ND	ND	ND	100
Conclusion	PASS	PASS	PASS	PASS	PASS	

Specimen No.	15	16	17	18	19	Total Limit (ppm)
Test Item	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	
Total Lead (Pb)	ND	ND	ND	ND	ND	100
Conclusion	PASS	PASS	PASS	PASS	PASS	

Note:

ppm (Parts per million) = mg/kg (Milligrams per kilogram)

LT = Less than

ND = Not detected (Reporting Limit = 20 ppm)

Composite results are based on specimen of least mass resulting in highest potential concentration.

**DETAILED RESULTS:****CPSIA Section 101, Total Lead in Substrate Materials**

Test Method: CPSC-CH-E1001-08.3 (Metal), CPSC-CH-E1002-08.3 (Non-Metal)

Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	20	21	22	23	24	Total Limit (ppm)
Test Item	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	
Total Lead (Pb)	ND	ND	ND	ND	ND	100
Conclusion	PASS	PASS	PASS	PASS	PASS	

Specimen No.	25	26	27	28	29	Total Limit (ppm)
Test Item	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	
Total Lead (Pb)	ND	ND	ND	89	ND	100
Conclusion	PASS	PASS	PASS	PASS	PASS	

Specimen No.	30	---	---	---	---	Total Limit (ppm)
Test Item	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	
Total Lead (Pb)	ND	---	---	---	---	100
Conclusion	PASS	---	---	---	---	

Note:

ppm (Parts per million) = mg/kg (Milligrams per kilogram)

LT = Less than

ND = Not detected (Reporting Limit = 20 ppm)

Composite results are based on specimen of least mass resulting in highest potential concentration.

**DETAILED RESULTS:****California Proposition 65, Total Lead in Substrate Materials**

Test Method: CPSC-CH-E1001-08.3 (Metal), CPSC-CH-E1002-08.3 (Non-Metal)
 Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	5	6	7	8	9	Total Limit (ppm)
Test Item	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	
Total Lead (Pb)	ND	ND	ND	ND	ND	100
Conclusion	PASS	PASS	PASS	PASS	PASS	

Specimen No.	10	11	12	13	14	Total Limit (ppm)
Test Item	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	
Total Lead (Pb)	ND	ND	ND	ND	ND	100
Conclusion	PASS	PASS	PASS	PASS	PASS	

Specimen No.	15	16	17	18	19	Total Limit (ppm)
Test Item	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	
Total Lead (Pb)	ND	ND	ND	ND	ND	100
Conclusion	PASS	PASS	PASS	PASS	PASS	

Note:

ppm (Parts per million) = mg/kg (Milligrams per kilogram)

LT = Less than

ND = Not detected (Reporting Limit = 20 ppm)

Composite results are based on specimen of least mass resulting in highest potential concentration.

Remark:

The specification is quoted from client's requirement.

**DETAILED RESULTS:****California Proposition 65, Total Lead in Substrate Materials**

Test Method: CPSC-CH-E1001-08.3 (Metal), CPSC-CH-E1002-08.3 (Non-Metal)
 Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	20	21	22	23	24	Total Limit (ppm)
Test Item	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	
Total Lead (Pb)	ND	ND	ND	ND	ND	100
Conclusion	PASS	PASS	PASS	PASS	PASS	

Specimen No.	25	26	27	28	29	Total Limit (ppm)
Test Item	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	
Total Lead (Pb)	ND	ND	ND	89	ND	100
Conclusion	PASS	PASS	PASS	PASS	PASS	

Specimen No.	30	---	---	---	---	Total Limit (ppm)
Test Item	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	
Total Lead (Pb)	ND	---	---	---	---	100
Conclusion	PASS	---	---	---	---	

Note:

ppm (Parts per million) = mg/kg (Milligrams per kilogram)

LT = Less than

ND = Not detected (Reporting Limit = 20 ppm)

Composite results are based on specimen of least mass resulting in highest potential concentration.

Remark:

The specification is quoted from client's requirement.

**DETAILED RESULTS:****California Proposition 65, Phthalates (DBP, BBP, DEHP, DINP, DIDP, DnHP)**

Test Method: CPSC-CH-C1001-09.3

Analytical Method: Gas Chromatography with Mass Spectrometry

Specimen No.		1	2	3	4	Limit (ppm)
Test Item	CAS No.	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	
Dibutyl phthalate (DBP)	84-74-2	LT 150	LT 130	LT 130	LT 260	1000
Benzyl butyl phthalate (BBP)	85-68-7	LT 150	LT 130	LT 130	LT 260	1000
Di-(2-ethylhexyl) phthalate (DEHP)	117-81-7	LT 150	LT 130	LT 130	LT 260	1000
Diisononyl phthalate (DINP)	28553-12-0 68515-48-0	LT 150	LT 130	LT 130	LT 260	1000
Diisodecyl phthalate (DIDP)	26761-40-0 68515-49-1	LT 150	LT 130	LT 130	LT 260	1000
Di-n-hexyl phthalate (DnHP)	84-75-3	LT 150	LT 130	LT 130	LT 260	1000
Conclusion		PASS	PASS	PASS	PASS	

Note:

ppm (Parts per million) = mg/kg (Milligrams per kilogram) = 0.0001 % m/m (Percent by mass)

LT = Less than

ND = Not detected (Reporting Limit = 120 ppm)

Composite results are based on specimen of least mass resulting in highest potential concentration.

Remark:

The specification is quoted from client's requirement.

**DETAILED RESULTS:****California Proposition 65, Phthalates (DBP, BBP, DEHP, DINP, DIDP, DnHP)**

Test Method: CPSC-CH-C1001-09.3

Analytical Method: Gas Chromatography with Mass Spectrometry

Specimen No.		5	6	7	8	Limit (ppm)
Test Item	CAS No.	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	
Dibutyl phthalate (DBP)	84-74-2	ND	ND	ND	ND	1000
Benzyl butyl phthalate (BBP)	85-68-7	ND	ND	ND	ND	1000
Di-(2-ethylhexyl) phthalate (DEHP)	117-81-7	ND	ND	ND	ND	1000
Diisononyl phthalate (DINP)	28553-12-0 68515-48-0	ND	ND	ND	ND	1000
Diisodecyl phthalate (DIDP)	26761-40-0 68515-49-1	ND	ND	ND	ND	1000
Di-n-hexyl phthalate (DnHP)	84-75-3	ND	ND	ND	ND	1000
Conclusion		PASS	PASS	PASS	PASS	

Note:

ppm (Parts per million) = mg/kg (Milligrams per kilogram) = 0.0001 % m/m (Percent by mass)

LT = Less than

ND = Not detected (Reporting Limit = 120 ppm)

Composite results are based on specimen of least mass resulting in highest potential concentration.

Remark:

The specification is quoted from client's requirement.

**DETAILED RESULTS:****California Proposition 65, Phthalates (DBP, BBP, DEHP, DINP, DIDP, DnHP)**

Test Method: CPSC-CH-C1001-09.3

Analytical Method: Gas Chromatography with Mass Spectrometry

Specimen No.		9	10	11	12	Limit (ppm)
Test Item	CAS No.	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	
Dibutyl phthalate (DBP)	84-74-2	ND	ND	ND	ND	1000
Benzyl butyl phthalate (BBP)	85-68-7	ND	ND	ND	ND	1000
Di-(2-ethylhexyl) phthalate (DEHP)	117-81-7	ND	ND	ND	ND	1000
Diisononyl phthalate (DINP)	28553-12-0 68515-48-0	ND	ND	ND	ND	1000
Diisodecyl phthalate (DIDP)	26761-40-0 68515-49-1	ND	ND	ND	ND	1000
Di-n-hexyl phthalate (DnHP)	84-75-3	ND	ND	ND	ND	1000
Conclusion		PASS	PASS	PASS	PASS	

Note:

ppm (Parts per million) = mg/kg (Milligrams per kilogram) = 0.0001 % m/m (Percent by mass)

LT = Less than

ND = Not detected (Reporting Limit = 120 ppm)

Composite results are based on specimen of least mass resulting in highest potential concentration.

Remark:

The specification is quoted from client's requirement.

**DETAILED RESULTS:****California Proposition 65, Phthalates (DBP, BBP, DEHP, DINP, DIDP, DnHP)**

Test Method: CPSC-CH-C1001-09.3

Analytical Method: Gas Chromatography with Mass Spectrometry

Specimen No.		13	14	15	16	Limit (ppm)
Test Item	CAS No.	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	
Dibutyl phthalate (DBP)	84-74-2	ND	ND	ND	ND	1000
Benzyl butyl phthalate (BBP)	85-68-7	ND	ND	ND	ND	1000
Di-(2-ethylhexyl) phthalate (DEHP)	117-81-7	ND	ND	ND	ND	1000
Diisononyl phthalate (DINP)	28553-12-0 68515-48-0	ND	ND	ND	ND	1000
Diisodecyl phthalate (DIDP)	26761-40-0 68515-49-1	ND	ND	ND	ND	1000
Di-n-hexyl phthalate (DnHP)	84-75-3	ND	ND	ND	ND	1000
Conclusion		PASS	PASS	PASS	PASS	

Note:

ppm (Parts per million) = mg/kg (Milligrams per kilogram) = 0.0001 % m/m (Percent by mass)

LT = Less than

ND = Not detected (Reporting Limit = 120 ppm)

Composite results are based on specimen of least mass resulting in highest potential concentration.

Remark:

The specification is quoted from client's requirement.

**DETAILED RESULTS:****California Proposition 65, Phthalates (DBP, BBP, DEHP, DINP, DIDP, DnHP)**

Test Method: CPSC-CH-C1001-09.3

Analytical Method: Gas Chromatography with Mass Spectrometry

Specimen No.		17	18	19	20	Limit (ppm)
Test Item	CAS No.	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	
Dibutyl phthalate (DBP)	84-74-2	ND	ND	ND	ND	1000
Benzyl butyl phthalate (BBP)	85-68-7	ND	ND	ND	ND	1000
Di-(2-ethylhexyl) phthalate (DEHP)	117-81-7	ND	ND	ND	ND	1000
Diisononyl phthalate (DINP)	28553-12-0 68515-48-0	ND	ND	ND	ND	1000
Diisodecyl phthalate (DIDP)	26761-40-0 68515-49-1	ND	ND	ND	ND	1000
Di-n-hexyl phthalate (DnHP)	84-75-3	ND	ND	ND	ND	1000
Conclusion		PASS	PASS	PASS	PASS	

Note:

ppm (Parts per million) = mg/kg (Milligrams per kilogram) = 0.0001 % m/m (Percent by mass)

LT = Less than

ND = Not detected (Reporting Limit = 120 ppm)

Composite results are based on specimen of least mass resulting in highest potential concentration.

Remark:

The specification is quoted from client's requirement.

**DETAILED RESULTS:****California Proposition 65, Phthalates (DBP, BBP, DEHP, DINP, DIDP, DnHP)**

Test Method: CPSC-CH-C1001-09.3

Analytical Method: Gas Chromatography with Mass Spectrometry

Specimen No.	21	22	23	---	Limit (ppm)
Test Item CAS No.	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	
Dibutyl phthalate (DBP) 84-74-2	ND	ND	ND	---	1000
Benzyl butyl phthalate (BBP) 85-68-7	ND	ND	ND	---	1000
Di-(2-ethylhexyl) phthalate (DEHP) 117-81-7	ND	ND	ND	---	1000
Diisononyl phthalate (DINP) 28553-12-0 68515-48-0	ND	ND	ND	---	1000
Diisodecyl phthalate (DIDP) 26761-40-0 68515-49-1	ND	ND	ND	---	1000
Di-n-hexyl phthalate (DnHP) 84-75-3	ND	ND	ND	---	1000
Conclusion	PASS	PASS	PASS	---	

Note:

ppm (Parts per million) = mg/kg (Milligrams per kilogram) = 0.0001 % m/m (Percent by mass)

LT = Less than

ND = Not detected (Reporting Limit = 120 ppm)

Composite results are based on specimen of least mass resulting in highest potential concentration.

Remark:

The specification is quoted from client's requirement.

**DETAILED RESULTS:****16 CFR 1307 Prohibition of Children's Toys and Child Care Articles Containing Specified Phthalates (DBP, BBP, DEHP, DINP, DHEXP / DnHP, DCHP, DIBP, DPENP)**

Test Method: CPSC-CH-C1001-09.3 (Modified) #

Analytical Method: Gas Chromatography with Mass Spectrometry

Specimen No.		1	2	3	4	Limit (ppm)
Test Item	CAS No.	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	
Dibutyl phthalate (DBP)	84-74-2	LT 150	LT 130	LT 130	LT 260	1000
Benzyl butyl phthalate (BBP)	85-68-7	LT 150	LT 130	LT 130	LT 260	1000
Di-(2-ethylhexyl) phthalate (DEHP)	117-81-7	LT 150	LT 130	LT 130	LT 260	1000
Diisononyl phthalate (DINP)	28553-12-0 68515-48-0	LT 150	LT 130	LT 130	LT 260	1000
Di-n-hexyl phthalate (DHEXP / DnHP)	84-75-3	LT 150	LT 130	LT 130	LT 260	1000
Dicyclohexyl phthalate (DCHP)	84-61-7	LT 150	LT 130	LT 130	LT 260	1000
Diisobutyl phthalate (DIBP)	84-69-5	LT 150	LT 130	LT 130	LT 260	1000
Di-n-pentyl phthalate (DPENP)	131-18-0	LT 150	LT 130	LT 130	LT 260	1000
Conclusion		PASS	PASS	PASS	PASS	

Note:

ppm (Parts per million) = mg/kg (Milligrams per kilogram) = 0.0001 % m/m (Percent by mass)

LT = Less than

ND = Not detected (Reporting Limit = 120 ppm)

Composite results are based on specimen of least mass resulting in highest potential concentration.

**DETAILED RESULTS:****16 CFR 1307 Prohibition of Children's Toys and Child Care Articles Containing Specified Phthalates (DBP, BBP, DEHP, DINP, DHEXP / DnHP, DCHP, DIBP, DPENP)**

Test Method: CPSC-CH-C1001-09.3 (Modified) #

Analytical Method: Gas Chromatography with Mass Spectrometry

Specimen No.		5	6	7	8	Limit (ppm)
Test Item	CAS No.	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	
Dibutyl phthalate (DBP)	84-74-2	ND	ND	ND	ND	1000
Benzyl butyl phthalate (BBP)	85-68-7	ND	ND	ND	ND	1000
Di-(2-ethylhexyl) phthalate (DEHP)	117-81-7	ND	ND	ND	ND	1000
Diisononyl phthalate (DINP)	28553-12-0 68515-48-0	ND	ND	ND	ND	1000
Di-n-hexyl phthalate (DHEXP / DnHP)	84-75-3	ND	ND	ND	ND	1000
Dicyclohexyl phthalate (DCHP)	84-61-7	ND	ND	ND	ND	1000
Diisobutyl phthalate (DIBP)	84-69-5	ND	ND	ND	ND	1000
Di-n-pentyl phthalate (DPENP)	131-18-0	ND	ND	ND	ND	1000
Conclusion		PASS	PASS	PASS	PASS	

Note:

ppm (Parts per million) = mg/kg (Milligrams per kilogram) = 0.0001 % m/m (Percent by mass)

LT = Less than

ND = Not detected (Reporting Limit = 120 ppm)

Composite results are based on specimen of least mass resulting in highest potential concentration.

**DETAILED RESULTS:****16 CFR 1307 Prohibition of Children's Toys and Child Care Articles Containing Specified Phthalates (DBP, BBP, DEHP, DINP, DHEXP / DnHP, DCHP, DIBP, DPENP)**

Test Method: CPSC-CH-C1001-09.3 (Modified) #

Analytical Method: Gas Chromatography with Mass Spectrometry

Specimen No.		9	10	11	12	Limit (ppm)
Test Item	CAS No.	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	
Dibutyl phthalate (DBP)	84-74-2	ND	ND	ND	ND	1000
Benzyl butyl phthalate (BBP)	85-68-7	ND	ND	ND	ND	1000
Di-(2-ethylhexyl) phthalate (DEHP)	117-81-7	ND	ND	ND	ND	1000
Diisononyl phthalate (DINP)	28553-12-0 68515-48-0	ND	ND	ND	ND	1000
Di-n-hexyl phthalate (DHEXP / DnHP)	84-75-3	ND	ND	ND	ND	1000
Dicyclohexyl phthalate (DCHP)	84-61-7	ND	ND	ND	ND	1000
Diisobutyl phthalate (DIBP)	84-69-5	ND	ND	ND	ND	1000
Di-n-pentyl phthalate (DPENP)	131-18-0	ND	ND	ND	ND	1000
Conclusion		PASS	PASS	PASS	PASS	

Note:

ppm (Parts per million) = mg/kg (Milligrams per kilogram) = 0.0001 % m/m (Percent by mass)

LT = Less than

ND = Not detected (Reporting Limit = 120 ppm)

Composite results are based on specimen of least mass resulting in highest potential concentration.

**DETAILED RESULTS:****16 CFR 1307 Prohibition of Children's Toys and Child Care Articles Containing Specified Phthalates (DBP, BBP, DEHP, DINP, DHEXP / DnHP, DCHP, DIBP, DPENP)**

Test Method: CPSC-CH-C1001-09.3 (Modified) #

Analytical Method: Gas Chromatography with Mass Spectrometry

Specimen No.		13	14	15	16	Limit (ppm)
Test Item	CAS No.	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	
Dibutyl phthalate (DBP)	84-74-2	ND	ND	ND	ND	1000
Benzyl butyl phthalate (BBP)	85-68-7	ND	ND	ND	ND	1000
Di-(2-ethylhexyl) phthalate (DEHP)	117-81-7	ND	ND	ND	ND	1000
Diisononyl phthalate (DINP)	28553-12-0 68515-48-0	ND	ND	ND	ND	1000
Di-n-hexyl phthalate (DHEXP / DnHP)	84-75-3	ND	ND	ND	ND	1000
Dicyclohexyl phthalate (DCHP)	84-61-7	ND	ND	ND	ND	1000
Diisobutyl phthalate (DIBP)	84-69-5	ND	ND	ND	ND	1000
Di-n-pentyl phthalate (DPENP)	131-18-0	ND	ND	ND	ND	1000
Conclusion		PASS	PASS	PASS	PASS	

Note:

ppm (Parts per million) = mg/kg (Milligrams per kilogram) = 0.0001 % m/m (Percent by mass)

LT = Less than

ND = Not detected (Reporting Limit = 120 ppm)

Composite results are based on specimen of least mass resulting in highest potential concentration.

**DETAILED RESULTS:****16 CFR 1307 Prohibition of Children's Toys and Child Care Articles Containing Specified Phthalates (DBP, BBP, DEHP, DINP, DHEXP / DnHP, DCHP, DIBP, DPENP)**

Test Method: CPSC-CH-C1001-09.3 (Modified) #

Analytical Method: Gas Chromatography with Mass Spectrometry

Specimen No.		17	18	19	20	Limit (ppm)
Test Item	CAS No.	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	
Dibutyl phthalate (DBP)	84-74-2	ND	ND	ND	ND	1000
Benzyl butyl phthalate (BBP)	85-68-7	ND	ND	ND	ND	1000
Di-(2-ethylhexyl) phthalate (DEHP)	117-81-7	ND	ND	ND	ND	1000
Diisononyl phthalate (DINP)	28553-12-0 68515-48-0	ND	ND	ND	ND	1000
Di-n-hexyl phthalate (DHEXP / DnHP)	84-75-3	ND	ND	ND	ND	1000
Dicyclohexyl phthalate (DCHP)	84-61-7	ND	ND	ND	ND	1000
Diisobutyl phthalate (DIBP)	84-69-5	ND	ND	ND	ND	1000
Di-n-pentyl phthalate (DPENP)	131-18-0	ND	ND	ND	ND	1000
Conclusion		PASS	PASS	PASS	PASS	

Note:

ppm (Parts per million) = mg/kg (Milligrams per kilogram) = 0.0001 % m/m (Percent by mass)

LT = Less than

ND = Not detected (Reporting Limit = 120 ppm)

Composite results are based on specimen of least mass resulting in highest potential concentration.

**DETAILED RESULTS:****16 CFR 1307 Prohibition of Children's Toys and Child Care Articles Containing Specified Phthalates (DBP, BBP, DEHP, DINP, DHEXP / DnHP, DCHP, DIBP, DPENP)**

Test Method: CPSC-CH-C1001-09.3 (Modified) #

Analytical Method: Gas Chromatography with Mass Spectrometry

Specimen No.		21	22	23	---	Limit (ppm)
Test Item	CAS No.	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	
Dibutyl phthalate (DBP)	84-74-2	ND	ND	ND	---	1000
Benzyl butyl phthalate (BBP)	85-68-7	ND	ND	ND	---	1000
Di-(2-ethylhexyl) phthalate (DEHP)	117-81-7	ND	ND	ND	---	1000
Diisononyl phthalate (DINP)	28553-12-0 68515-48-0	ND	ND	ND	---	1000
Di-n-hexyl phthalate (DHEXP / DnHP)	84-75-3	ND	ND	ND	---	1000
Dicyclohexyl phthalate (DCHP)	84-61-7	ND	ND	ND	---	1000
Diisobutyl phthalate (DIBP)	84-69-5	ND	ND	ND	---	1000
Di-n-pentyl phthalate (DPENP)	131-18-0	ND	ND	ND	---	1000
Conclusion		PASS	PASS	PASS	---	

Note:

ppm (Parts per million) = mg/kg (Milligrams per kilogram) = 0.0001 % m/m (Percent by mass)

LT = Less than

ND = Not detected (Reporting Limit = 120 ppm)

Composite results are based on specimen of least mass resulting in highest potential concentration.

**DETAILED RESULTS:****Canadian Toys Regulations SOR/2011-17 as Amended, Item 23 –
Leachable Elements in Paints and Surface Coatings**

Test Method: Health Canada Method C-03 (Effective 2014-02-20)

Analytical Method: Inductively Coupled Plasma-Mass Spectrometry

Specimen No.	1	2	3	4	---	Leachable
Test Item	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	Limit (ppm)
Leachable Antimony (Sb)	ND	ND	ND	ND	---	1000
Leachable Arsenic (As)	ND	ND	ND	ND	---	1000
Leachable Barium (Ba)	ND	ND	ND	ND	---	1000
Leachable Cadmium (Cd)	ND	ND	ND	ND	---	1000
Leachable Selenium (Se)	ND	ND	ND	ND	---	1000
Conclusion	PASS	PASS	PASS	PASS	---	

Note:

ppm (Parts per million) = mg/kg (Milligrams per kilogram)

LT = Less than

ND = Not detected (Reporting Limit = 50 ppm)

**DETAILED RESULTS:****Canadian Toys Regulations SOR/2011-17 as Amended, Item 23 –
Total Lead and Mercury in Paints and Surface Coatings**

Test Method: ASTM F963-17 Clause 8.3.1

Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	1	2	3	4	---	Total Limit (ppm)
Test Item	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	
Total Lead (Pb)	ND	ND	ND	ND	---	90
Total Mercury (Hg)	ND	ND	ND	ND	---	10
Conclusion	PASS	PASS	PASS	PASS	---	

Note:

ppm (Parts per million) = mg/kg (Milligrams per kilogram)

LT = Less than

ND = Not detected (Reporting Limit = 10 ppm)

Composite results are based on specimen of least mass resulting in highest potential concentration.

**DETAILED RESULTS:****Canadian Consumer Products Containing Lead Regulations (SOR/2018-83), Total Lead Content**

Test Method: ASTM F963-17 Clause 8.3.1

Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	1	2	3	4	5	Limit (mg/kg)
Test Item	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	
Total Lead (Pb)	ND	ND	ND	ND	ND	90
Conclusion	PASS	PASS	PASS	PASS	PASS	

Specimen No.	6	7	8	9	10	Limit (mg/kg)
Test Item	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	
Total Lead (Pb)	ND	ND	ND	ND	ND	90
Conclusion	PASS	PASS	PASS	PASS	PASS	

Specimen No.	11	12	13	14	15	Limit (mg/kg)
Test Item	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	
Total Lead (Pb)	ND	ND	ND	ND	ND	90
Conclusion	PASS	PASS	PASS	PASS	PASS	

Note:

mg/kg (Milligrams per kilogram) = ppm (Parts per million) = 0.0001 % m/m (Percent by mass)

LT = Less than

ND = Not detected (Reporting Limit = 20 ppm)

Composite results are based on specimen of least mass resulting in highest potential concentration.

**DETAILED RESULTS:****Canadian Consumer Products Containing Lead Regulations (SOR/2018-83), Total Lead Content**

Test Method: ASTM F963-17 Clause 8.3.1

Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	16	17	18	19	20	Limit (mg/kg)
Test Item	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	
Total Lead (Pb)	ND	ND	ND	ND	ND	90
Conclusion	PASS	PASS	PASS	PASS	PASS	

Specimen No.	21	22	23	24	25	Limit (mg/kg)
Test Item	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	
Total Lead (Pb)	ND	ND	ND	ND	ND	90
Conclusion	PASS	PASS	PASS	PASS	PASS	

Specimen No.	26	27	28	29	30	Limit (mg/kg)
Test Item	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	
Total Lead (Pb)	ND	ND	89	ND	ND	90
Conclusion	PASS	PASS	PASS	PASS	PASS	

Note:

mg/kg (Milligrams per kilogram) = ppm (Parts per million) = 0.0001 % m/m (Percent by mass)

LT = Less than

ND = Not detected (Reporting Limit = 20 ppm)

Composite results are based on specimen of least mass resulting in highest potential concentration.

**DETAILED RESULTS:****CPSIA Section 106, Mandatory Toy Safety Standard ASTM F963-17, Mechanical Hazards
16 CFR 1500, Federal Hazardous Substances Act (FHSA), Mechanical Hazards**

Mechanical hazards evaluated as described in 16 CFR 1500.51-1500.53 and ASTM F963-17, as applicable.

Test	Observation	Conclusion
Impact	No Sharp Edge or Sharp Point	PASS
Torque	No Sharp Edge or Sharp Point	PASS
Tension	No Sharp Edge or Sharp Point	PASS

Other Applicable ASTM F963-17 Sections

Section	Test	Conclusion
4.1	Material Quality	PASS
4.7	Accessible Edges	PASS
4.9	Accessible Points	PASS

16 CFR 1500.44 and ASTM F963-17, Section 4.2, Flammability of Solids

Test	Observation	Conclusion
Flammability of Solids	No Ignition	PASS

19 CFR 134.11, Country of Origin[#]

Test	Observation	Conclusion
Country of Origin	Present on packaging and can be read easily by consumer at the point of sale	PASS

**DETAILED RESULTS:****Canadian Toy Regulations SOR/2011-17 as Amended by SOR/2016-195& SOR/2016-302, Mechanical Hazards Requirements**

Test	Observation	Conclusion
Impact	No Sharp Edge or Sharp Point	PASS
Push/Pull	No Sharp Edge or Sharp Point	PASS

Section	Requirement	Conclusion
8	Metal Edges	PASS
10	Plastic Edges	PASS

Canadian Toy Regulations SOR/2011-17 as Amended by SOR/2016-195& SOR/2016-302, Item 21 Celluloid or Cellulose Nitrate

(Method: Visual Observation)

Test	Observation	Conclusion
Cellulose Nitrate	No visual signs of Cellulose Nitrate.	PASS

**SPECIMEN DESCRIPTION:**

Specimen No.	Specimen Description	Location
1	Black coating	On spinner (all Fidget pen styles/ Caps off WH style)
2	Grey coating	On spinner (all Hyper styles except white/ all Caps off styles except WH style)
3	Bright grey coating	On conned tip/ ring/ on push button (all Fidget pen styles)
4	Light grey coating	On end of barrel (all Fidget pen styles)
5	Black plastic	Spinner/ cap (Caps off BK/ Fidget pen Bk styles)
6	Blue plastic	Spinner/ cap (Caps off BL/ Fidget pen BL styles)
7	Red plastic	Spinner/ cap (Caps off RD/ Fidget pen RD style)
8	Translucent plastic	Spinner/ cap (Caps off Glow style)
9	White plastic	Spinner/ cap (Caps off WH style)
10	Dull red plastic	Spinner/ cap (Hyper RD style)
11	Dull black plastic	Spinner/ cap (Hyper Bk style)
12	Dull white plastic	Spinner/ cap (all Hyper/ Hyper WH style)
13	Dull blue plastic	Spinner/ cap (Hyper BL style)
14	Off white plastic	Conned tip/ push button/ end of barrel/ ring (all Fidget pen styles)
15	Green plastic	Spinner (Fidget pen GR style)
16	Orange plastic	Spinner (Fidget pen OR style)
17	Bright blue plastic	Barrel (Fidget pen BL style)
18	Bright black plastic	Barrel (Fidget pen BK style)
19	Bright red plastic	Barrel (Fidget pen RD style)
20	Bright green plastic	Barrel (Fidget pen GR style)
21	Bright orange plastic	Barrel (Fidget pen OR style)
22	White plastic	Ink refill (all Fidget pen styles)
23	Translucent plastic	Connector of ink refill (all Fidget pen styles)

ANSECO GROUP (HK) LIMITED ♦ 3/F Liven House ♦ No. 61 – 63 King Yip Street ♦ Kwun Tong ♦ Kowloon ♦ Hong Kong ♦ Tel: (852)3185 8000

The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.

The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.

This test report may not be reproduced in whole or in part, without written approval of ANSECO Group (HK) Limited.

ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.

**SPECIMEN DESCRIPTION:**

Specimen No.	Specimen Description	Location
24	Black ink	Ink (all Fidget pen styles)
25	Bright silvery metal	Opener (all Caps off styles)
26	Dull silvery metal	Spring (all Fidget pen styles)
27	Matt silvery metal	Spinner (all Fidget pen styles)
28	Off silvery metal	Tip with ball (all Fidget pen styles)
29	Slivery metal	Large ring of inner bearing (all Hyper styles)
30	Dull slivery metal	Small ring of inner bearing (all Hyper styles)



Test Report #

18H-008788

Pages:

Page 35 of 35

SAMPLE PHOTO:



-End Report-

ANSECO GROUP (HK) LIMITED ♦ 3/F Liven House ♦ No. 61 – 63 King Yip Street ♦ Kwun Tong ♦ Kowloon ♦ Hong Kong ♦ Tel: (852)3185 8000

The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.

The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.

This test report may not be reproduced in whole or in part, without written approval of ANSECO Group (HK) Limited.

ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.